

AT



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number: **0 548 448 A1**

EUROPEAN PATENT APPLICATION

Application number: **92106519.9**

Int. Cl.⁵: **A61K 9/50, A61K 9/54**

Date of filing: **15.04.92**

Priority: **24.12.91 US 814111**

Date of publication of application:
30.06.93 Bulletin 93/26

Designated Contracting States:
AT BE CH DE DK ES FR GB GR IT LI LU NL PT SE

Applicant: **Euro-Celtique S.A.**
122 Boulevard de la Petrusse
Luxemburg(LU)


Inventor: **Oshlack, Benjamin**

354 East 84th Street
New York, New York 10028(US)
Inventor: **Pedi, Frank**
2773 Hyatt Street
Yorktown Heights, New York 10598(US)
Inventor: **Chasin, Mark**
3 Wayne Court
Manalapan, New Jersey 07726(US)

Representative: **Strasse, Malwald, Meys, Stach & Vonnemann**
Balanstrasse 55
W-8000 München 90 (DE)

Stabilized controlled release substrate having a coating derived from an aqueous dispersion of hydrophobic polymer.

A stabilized solid controlled release dosage form having a coating derived from an aqueous dispersion of ethylcellulose is obtained by overcoating a substrate including a therapeutically active with an aqueous dispersion of ethylcellulose and then curing the coated substrate at a temperature and relative humidity elevated to a suitable level above ambient conditions until the coated dosage form attains a stabilized dissolution profile substantially unaffected by exposure to storage conditions of elevated temperature and/or elevated relative humidity.



EP 0 548 448 A1

BACKGROUND OF THE INVENTION

It is the aim of all controlled release preparations to provide a longer duration of pharmacological response after the administration of the dosage form than is ordinarily experienced after the administration of an immediate release dosage form. Such extended periods of response provides for many inherent therapeutic benefits that are not achieved with short acting, immediate release products.

Controlled release formulations known in the art include specially coated beads or pellets, coated tablets and ion exchange resins, wherein the slow release of the active drug is brought about through selective breakdown of, or permeation through, the coating of the preparation or through formulation with a special matrix to affect the release of the drug.

An important aspect of all forms of controlled release dosage forms is related to the stability of the same. The stability of a pharmaceutical dosage form is related to maintaining its physical, chemical, microbiological, therapeutic, pharmaceutical, and toxicological properties when stored, i.e., in a particular container and environment. Stability study requirements are covered, e.g., in the Good Manufacturing Practices (GMPs), the U.S.P., as well as in New Drug Applications (NDAs) and Investigational New Drug Applications (INDs).

The ingredients used in sustained release dosage formulations often present special problems with regard to their physical stability during storage. For example, waxes which have been used in such formulations are known to undergo physical alterations on prolonged standing, thus precautions are taken to stabilize them at the time of manufacture or to prevent the change from occurring. Fats and waxy materials when used in purified states are known to crystallize in unstable forms, causing unpredictable variations in availability rates during stability testing at the time of manufacture and during later storage.

It is known that certain strategies can be undertaken to obtain stabilized controlled release formulations in many cases, such as insuring that the individual ingredients are in a stable form before they are incorporated into the product, and that processing does not change this condition, retarding the instability by including additional additives, and inducing the individual ingredients of the dosage form to reach a stable state before the product is finally completed.

It is also recognized that the moisture content of the product can also influence the stability of the product. Changes in the porosity and/or hydration level of a polymeric film, such as the ethyl celluloses, can alter the rate of water permeation and drug availability. Also, binders such as acacia are known to become less soluble when exposed to moisture and heat. Such problems have been handled by controls in the processing method and proper packaging of the product.

Hydrophobic polymers such as certain cellulose derivatives, zein, acrylic resins, waxes, higher aliphatic alcohols, and polylactic and polyglycolic acids have been used in the prior art to develop controlled release dosage forms. Methods of using these polymers to develop controlled release dosage forms such as tablets, capsules, suppositories, spheroids, beads or microspheres are to overcoat the individual dosage units with these hydrophobic polymers. It is known in the prior art that these hydrophobic coatings can be applied either from a solution, suspension or dry. Since most of these polymers have a low solubility in water, they are usually applied by dissolving the polymer in an organic solvent and spraying the solution onto the individual drug forms (such as beads or tablets) and evaporating off the solvent.

Aqueous dispersions of hydrophobic polymers have been used in the prior art to coat pharmaceutical dosage forms for aesthetic reasons such as film coating tablets or beads or for taste-masking. However, these dosage forms are used for immediate release administration of the active drug contained in the dosage form.

The use of organic solvents in the preparation of polymer coatings is considered problematic as the formulations have inherent problems with regard to flammability, carcinogenicity, and safety in general. In addition, the use of organic solvents is disfavored due to environmental concerns.

Therefore, it is desirable to prepare a controlled release formulation prepared from an aqueous dispersion of a hydrophobic polymer. However, to date, attempts to prepare stable controlled release pharmaceutical formulations using aqueous dispersions of hydrophobic polymers have been unsuccessful due to stability problems. In particular, when coating these pharmaceutical forms using aqueous polymeric dispersions to obtain a desired release profile of the active drug(s) over several hours or longer, it is known in the art that the dissolution release profile changes on ageing. It is also known that this instability problem does not exist when the polymers are applied from organic solvent solution.

For example, Dressman, et al., *Proceed. Intern. Symp. Control. Rel. Bioact. Mater.*, 18 (1991), pp. 654-655, Controlled Release Society, Inc. reported on tests conducted which showed that phenylpropanolamine HCl pellets coated with an ethyl cellulose-based film are only stable at room temperature under ambient humidity conditions. In these experiments, phenylpropanolamine HCl was overlaid on sugar seeds to a 76%

loading, and coated with 10% ethyl cellulose applied from an aqueous dispersion. A second sample consisted of phenylpropanolamine spheronized with microcrystalline cellulose in a 70:30 ratio, then coated with 15% ethyl cellulose applied from an aqueous dispersion. Samples from each batch were stored for up to four weeks under conditions of room temperature/ambient humidity; room temperature/high humidity (75% RH); 37 °C/ambient humidity; and 37 °C/high humidity. The data for the dissolution profiles indicated that the lag time and percent drug released at 8 hours were unstable at all conditions other than room temperature/ambient humidity conditions.

Although the authors considered the pellets to be unaffected by storage conditions, they concluded that the release mechanism from the phenylpropanolamine HCl pellets overcoated with ethyl cellulose-based films appear to depend upon the pellet composition, and that under high relative humidity storage, the rate of release may be effected, especially if the samples were stored at elevated temperature.

Munday, et al., Drug Devel. and Indus. Phar., 17 (15) 2135-2143 (1991) report that film coated theophylline mini-tablets film coated with ethyl cellulose with PEG (2:1), and ethyl cellulose with Eudragit L (2:1) proved to have impeded dissolution upon storage under stress conditions, the degree of slowdown of release being said to be directly proportional to temperature, while the effect of relative humidity (RH) appeared to be insignificant.

The authors concluded therein that the decreased rate of release was due to the slowing in the rate of molecular diffusion of the drug across the polymeric coating material, and suggested that the change was due to significant alterations in the permeability of the polymer which occurred during the experimental storage.

Aqueous polymeric dispersions have been used to produce stable controlled release dosage forms, but this has only been possible by other methods such as incorporation of the same into the matrix of the dosage form, rather than via the use of a coating of the aqueous polymeric dispersion to obtain retardant properties.

OBJECTS AND SUMMARY OF THE INVENTION

It is therefore an object of the present invention to provide a controlled release dosage form for oral administration which comprises a coating of an aqueous dispersion of a hydrophobic polymer which is substantially stable despite exposure to elevated temperatures and/or elevated humidity levels during storage.

It is a further object of the present invention to provide a controlled release dosage form prepared with an overcoat of an aqueous dispersion of a hydrophobic polymer which is substantially stable under stress conditions, including even extended periods of high temperature and high humidity.

These objects and others have been accomplished by the present invention, which relates to a solid dosage form which has a controlled release overcoat derived from an aqueous dispersion of a hydrophobic polymer which provides a substantially stable release pattern of a therapeutically active agent(s) contained therein.

The present invention further relates to the surprising discovery that when the coated formulation is exposed to certain elevated or "stressed" conditions of temperature and humidity for a certain amount of time, a desired endpoint may be attained whereat the release rate of the therapeutically active agent does not substantially change upon ageing under a wide range of temperature and/or humidity conditions. This surprising discovery makes it possible to use aqueous dispersions of hydrophobic polymers for coating pharmaceutical dosage forms to produce stable controlled release pharmaceutical products.

The present invention is also related to a solid dosage form comprising a core comprising a therapeutically active agent and an overcoating derived from an aqueous dispersion of ethylcellulose in an amount sufficient to obtain a controlled release of the therapeutically active agent when the dosage form is exposed to aqueous solutions, e.g. gastric fluid. The solid dosage form is cured after the overcoating is applied such that the release of the therapeutically active agent is substantially unaffected by exposure to elevated temperature and/or humidity.

The present invention is also related to a stabilized controlled release solid dosage form for oral administration, comprising a plurality of inert pharmaceutically acceptable beads coated with a therapeutically active agent, and an ethylcellulose overcoat of a suitable thickness to obtain a controlled release of said therapeutically active agent when the solid dosage form is exposed to aqueous solutions, the ethylcellulose overcoat being derived from an aqueous dispersion of ethylcellulose with an effective amount of a suitable plasticizing agent. The ethylcellulose coated beads are cured under stress conditions, i.e. at a temperature and relative humidity elevated to a suitable level above ambient conditions to attain a finished product which has a dissolution profile which is substantially unaffected by exposure to storage

conditions of elevated temperature and/or humidity.

The present invention is further related to a stabilized solid controlled dosage form comprising a therapeutically active agent overcoated with an aqueous dispersion of ethylcellulose and cured at conditions of temperature and relative humidity greater than ambient conditions until a stabilized dissolution profile substantially unaffected by exposure to storage conditions of elevated temperature and/or elevated relative humidity is obtained.

The present invention is also related to a method for obtaining a stabilized controlled release formulation comprising a substrate coated with an aqueous dispersion of a hydrophobic polymer, comprising preparing an aqueous dispersion of ethylcellulose, preparing a substrate comprising a therapeutically active agent, overcoating the substrate with a sufficient amount of the aqueous dispersion of ethylcellulose to obtain a predetermined controlled release of the therapeutically active agent when the coated particles are exposed to aqueous solutions, and curing the coated substrate under stressed conditions by subjecting said coated particles to greater than ambient temperature and humidity and continuing the curing until an endpoint is reached at which the coated substrate attains a dissolution profile which is substantially unaffected by exposure to storage conditions of elevated temperature and/or humidity.

In a further embodiment, the method further includes the step of determining the endpoint for a particular formulation by exposing the formulation to various stages of the above-mentioned curing and obtaining dissolution profiles for the formulation until the dissolution profiles of the formulation are substantially stabilized. The formulation is then modified, if necessary, to obtain a desired dissolution profile of the therapeutically active agent based on the end point.

DETAILED DESCRIPTION

Ethylcellulose, which is a cellulose ether that is formed by the reaction of ethyl chloride with alkaline cellulose, is completely insoluble in water and gastrointestinal juices, and therefore to date has been considered not to be suitable by itself for tablet coating. It has, however, been commonly used in combination with hydroxypropyl methylcellulose and other film-formers to toughen or influence the dissolution rate of the film. Due to the solubility characteristics of ethylcellulose, this polymer has been mainly applied to the above-mentioned formulations from organic solutions.

Many polymers have been investigated for use in film-coating. Most film-coats are prepared by deposition of one or more film-forming polymers resulting in coats that usually represent no more than about 2-5% by weight of the final coated product. The film-coating has been used in conjunction with the preparation of tablets, pills, capsules, granules, and powders. The characteristics of the polymer used in the film-coating is governed by the structure, size and properties of its macromolecules. Common film-formers used in pharmaceuticals as nonenteric materials include hydroxypropyl methylcellulose, methyl hydroxyethylcellulose, hydroxypropylcellulose, sodium carboxymethylcellulose, ethylcellulose, and others.

In order to obtain a controlled release formulation, it is usually necessary to overcoat the substrate comprising the therapeutically active agent with a sufficient amount of the aqueous dispersion of ethylcellulose to obtain a weight gain level from about 5 to about 15 percent, although the overcoat may be lesser or greater depending upon the physical properties of the therapeutically active agent and the desired release rate, the inclusion of plasticizer in the aqueous dispersion of ethylcellulose and the manner of incorporation of the same, for example.

An example of a suitable controlled release formulation pursuant to the present invention will provide a dissolution rate in vitro of the dosage form, when measured by the USP Paddle Method at 100 rpm in 900 ml aqueous buffer (pH between 1.6 and 7.2) at 37° C, is between 12.5 and 42.5% (by wt) therapeutically active agent released after 1 hour, between 25 and 55% (by wt) released after 2 hours, between 45 and 75% (by wt) released after 4 hours and between 55 and 85% (by wt) released after 6 hours. This example is, of course, not intended to be limiting in any manner whatsoever.

The aqueous dispersions of hydrophobic polymers used as coatings in the present invention may be used in conjunction with tablets, spheroids (or beads), microspheres, seeds, pellets, ion-exchange resin beads, and other multi-particulate systems in order to obtain a desired controlled release of the therapeutically active agent. Granules, spheroids, or pellets, etc., prepared in accordance with the present invention can be presented in a capsule or in any other suitable dosage form.

Because ethylcellulose has a relatively high glass transition temperature and does not form flexible films under normal coating conditions, it is necessary to plasticize the ethylcellulose before using the same as a coating material.

One commercially-available aqueous dispersion of ethylcellulose is Aquacoat® (FMC Corp., Philadelphia, Pennsylvania, U.S.A.). Aquacoat® is prepared by dissolving the ethylcellulose in a water-immiscible

organic solvent and then emulsifying the same in water in the presence of a surfactant and a stabilizer. After homogenization to generate submicron droplets, the organic solvent is evaporated under vacuum to form a pseudolatex. The plasticizer is not incorporated in the pseudolatex during the manufacturing phase. Thus, prior to using the same as a coating, it is necessary to intimately mix the Aquacoat® with a suitable plasticizer prior to use.

With respect to handling and storage conditions, FMC states that Aquacoat® will undergo a rise in viscosity upon prolonged exposure to temperatures below 15°C or above 35°C, and that viscosity can be reduced to less than 100 cps by applying shear (e.g., propeller type mixer). FMC further states that a continuous film may be formed through a process known as gradual coalescence wherein the individual latex particles coalesce to form a continuous film of plasticized ethylcellulose polymer. After this period, the properties are said to remain constant. Higher coating temperatures, or a high temperature "curing" step is said by FMC to accelerate the process. If the coalescence process is not complete, FMC states that variability in release rates will result.

However, as will be demonstrated by the examples provided herein, it has been found that curing the film coating simply by utilizing a higher coating temperature or a high temperature curing step will not effectively stabilize the dissolution profile of the product upon storing.

Another aqueous dispersion of ethylcellulose is commercially available as Surelease® (Colorcon, Inc., West Point, Pennsylvania, U.S.A.). This product is prepared by incorporating plasticizer into the dispersion during the manufacturing process. A hot melt of a polymer, plasticizer (dibutyl sebacate), and stabilizer (oleic acid) is prepared as a homogeneous mixture, which is then diluted with an alkaline solution to obtain an aqueous dispersion which can be applied directly onto substrates.

The coating formulations of the present invention should be capable of producing a strong, continuous film that is smooth and elegant, capable of supporting pigments and other coating additives, non-toxic, inert, and tack-free.

It is preferred that the aqueous dispersion of ethylcellulose used in the present invention include an effective amount of a suitable plasticizing agent, as it has been found that the use of a plasticizer will further improve the physical properties of the film. The plasticization of the ethylcellulose may be accomplished either by so-called "internal plasticization" and "external plasticization."

Internal plasticization usually pertains directly to molecular modifications of the polymer during its manufacture, e.g., by copolymerization, such as altering and/or substituting functional groups, controlling the number of side chains, or controlling the length of the polymer. Such techniques are usually not performed by the formulator of the coating solution.

External plasticization involves the addition of a material to a film solution so that the requisite changes in film properties of the dry film can be achieved.

The suitability of a plasticizer depends on its affinity or solvating power for the polymer and its effectiveness at interfering with polymer-polymer attachments. Such activity imparts the desired flexibility by relieving molecular rigidity. Generally, the amount of plasticizer included in a coating solution is based on the concentration of the film-former, e.g., most often from about 1 to about 50 percent by weight of the film-former. Concentration of the plasticizer, however, can only be properly determined after careful experimentation with the particular coating solution and method of application.

An important parameter in the determination of a suitable plasticizer for a polymer is related to the glass transition temperature (T_g) of the polymer. The glass transition temperature is related to the temperature or temperature range where there is a fundamental change in the physical properties of the polymer. This change does not reflect a change in state, but rather a change in the macromolecular mobility of the polymer.

Below the T_g, the polymer chain mobility is severely restricted. Thus, for a given polymer, if its T_g is above room temperature, the polymer will behave as a glass, being hard, non-pliable and rather brittle, properties which could be somewhat restrictive in film coating since the coated dosage form may be subjected to a certain amount of external stress.

Incorporation of suitable plasticizers into the polymer matrix effectively reduces the T_g, so that under ambient conditions the films are softer, more pliable and often stronger, and thus better able to resist mechanical stress.

Other aspects of suitable plasticizers include the ability of the plasticizer to act as a good "swelling agent" for the ethylcellulose, and the insolubility of the plasticizer in water.

Examples of suitable plasticizers include water insoluble plasticizers such as dibutyl sebacate, diethyl phthalate, triethyl citrate, tributyl citrate, and triacetin, although it is possible that other water-insoluble plasticizers (such as acetylated monoglycerides, phthalate esters, castor oil, etc.) may be used. Triethyl citrate is an especially preferred plasticizer for the aqueous dispersions of ethyl cellulose of the present

invention.

The stabilized controlled release formulations of the present invention slowly release the therapeutically active agent, e.g., when ingested and exposed to gastric fluids, and then to intestinal fluids. The controlled release profile of the formulations of the invention can be altered, for example, by varying the amount of overcoating with the aqueous dispersion of ethylcellulose, altering the manner in which the plasticizer is added to the aqueous dispersion of ethylcellulose, by varying the amount of plasticizer relative to ethylcellulose, by the inclusion of additional ingredients or excipients, by altering the method of manufacture, etc.

A wide variety of therapeutically active agents can be used in conjunction with the present invention. The therapeutically active agents (e.g. pharmaceutical agents) which may be used in the compositions of the present invention include both water soluble and water insoluble drugs. Examples of such therapeutically active agents include antihistamines (e.g., dimenhydrinate, diphenhydramine, chlorpheniramine and dexchlorpheniramine maleate), analgesics (e.g., aspirin, codeine, morphine, dihydromorphone, oxycodone, etc.), anti-inflammatory agents (e.g., naproxyn, diclofenac, indomethacin, ibuprofen, acetaminophen, aspirin, sulindac), gastro-intestinals and anti-emetics (e.g., metoclopramide), anti-epileptics (e.g., phenytoin, meprobamate and nitrazepam), vasodilators (e.g., nifedipine, papaverine, diltiazem and nicardirine), anti-tussive agents and expectorants (e.g., codeine phosphate), anti-asthmatics (e.g. theophylline), anti-spasmodics (e.g. atropine, scopolamine), hormones (e.g., insulin, leparin), diuretics (e.g., elacrylic acid, bendrofluazide), anti-hypotensives (e.g., propranolol, clonidine), bronchodilators (e.g., albuterol), anti-inflammatory steroids (e.g., hydrocortisone, triamcinolone, prednisone), antibiotics (e.g., tetracycline), antihemorrhoidals, hypnotics, psychotropics, antidiarrheals, mucolytics, sedatives, decongestants, laxatives, antacids, vitamins, stimulants (including appetite suppressants such as phenylpropanolamine). The above list is not meant to be exclusive.

In certain preferred embodiments, the therapeutically active agent comprises hydromorphone, oxycodone, dihydrocodeine, codeine, dihydromorphone, morphine, buprenorphine, salts of any of the foregoing, and mixtures of any of the foregoing, and the like.

When the aqueous dispersion of ethylcellulose is used to coat inert pharmaceutical beads such as nu pariel 18/20 beads, a plurality of the resultant stabilized solid controlled release beads may thereafter be placed in a gelatin capsule in an amount sufficient to provide an effective controlled release dose when ingested and contacted by gastric fluid. In this embodiment, beads coated with a therapeutically active agent are prepared, e.g. by dissolving the therapeutically active agent in water and then spraying the solution onto a substrate, for example, nu pariel 18/20 beads, using a Wurster insert. Optionally, additional ingredients are also added prior to coating the beads in order to assist the hydromorphone binding to the beads, and/or to color the solution, etc. For example, a product which includes hydroxypropyl methylcellulose, etc. with or without colorant may be added to the solution and the solution mixed (e.g., for about 1 hour) prior to application of the same onto the beads. The resultant coated substrate, in this example beads, may then be optionally overcoated with a barrier agent, to separate the therapeutically active agent from the ethylcellulose coating. An example of a suitable barrier agent is one which comprises hydroxypropyl methylcellulose. However, any film-former known in the art may be used. It is preferred that the barrier agent does not affect the dissolution rate of the final product.

The hydromorphone, HPMC protected (optional) beads may then be overcoated with an aqueous dispersion of ethylcellulose. The aqueous dispersion of ethylcellulose preferably further includes an effective amount of plasticizer, e.g. triethyl citrate. Pre-formulated aqueous dispersions of ethylcellulose, such as Aquacoat® or Surelease®, may be used. If Surelease® is used, it is not necessary to separately add a plasticizer.

The coating solutions of the present invention preferably contain, in addition to the film-former, plasticizer, and solvent system (i.e., water), a colorant to provide elegance and product distinction. Color may be added to the solution of the therapeutically active agent instead, or in addition to the aqueous dispersion of ethylcellulose. For example, color be added to Aquacoat® via the use of alcohol or propylene glycol based color dispersions, milled aluminum lakes and opacifiers such as titanium dioxide by adding color with shear to water soluble polymer solution and then using low shear to the plasticized Aquacoat®. Alternatively, any suitable method of providing color to the formulations of the present invention may be used.

The plasticized aqueous dispersion of ethylcellulose may be applied onto the substrate comprising the therapeutically active agent by spraying using any suitable spray equipment known in the art. A sufficient amount of the aqueous dispersion of ethylcellulose to obtain a predetermined controlled release of said therapeutically active agent when said coated substrate is exposed to aqueous solutions, e.g. gastric fluid, is preferably applied, taking into account the physical characteristics of the therapeutically active agent,

the manner of incorporation of the plasticizer, etc. After coating with Aquacoat®, a further overcoat of a film-former, such as Opadry®, is optionally applied to the beads. This overcoat is provided, if at all, in order to substantially reduce agglomeration of the beads.

Next, the coated beads are cured in order to obtain a stabilized release rate of the therapeutically active agent. Curing is traditionally carried out, if at all, via a forced-air oven at 60 °C for anywhere from 2-24 hours. This standard curing does not stabilize the dissolution profile of the formulation, as will be demonstrated by the examples set forth herein.

The curing step pursuant to the present invention is accomplished by subjecting the coated beads to "stressed conditions" by subjecting said coated substrate to greater than normal, ambient (i.e., room) temperature and relative humidity and continuing the curing until an endpoint is reached at which the coated beads attain a dissolution profile which is substantially unaffected by further exposure to storage conditions of elevated temperature and/or humidity. More particularly, the coated substrates of the present invention should be cured at a temperature greater than the glass transition temperature of the coating solution (i.e., ethylcellulose) and at a greater than ambient humidity.

One possible mechanism for the change in the dissolution profile of prior art products cured by the standard methods, i.e. curing for 2 hours or more at 60 °C dry heat, is that these products continue to cure during storage, and may never reach a stabilized end-point at which the product provides a substantially constant dissolution profile. In contrast, the cured products of the present invention provide a release rate of the therapeutically active agent which is substantially unaffected during storage by elevations in temperature and humidity.

In preferred embodiments of the present invention, the stabilized product is obtained by subjecting the coated substrate to oven curing at elevated temperature/humidity levels for the required time period, the optimum values for temperature, humidity and time for the particular formulation being determined experimentally.

In certain embodiments of the present invention, the stabilized product is obtained via an oven curing conducted at a temperature of about 60 °C and a relative humidity from about 60% to about 100% for a time period from about 48 to about 72 hours. This is the case for the hydromorphone beads described in the examples provided below. However, one skilled in the art will recognize that necessary curing conditions may be changed somewhat, and may in fact be broader than the above-mentioned temperature, humidity and time ranges, depending upon the particular formulation, in order to obtain a stabilized product.

When the controlled release coating of the present invention is to be applied to tablets, the tablet core (e.g. the substrate) may comprise the active agent along with any pharmaceutically accepted inert pharmaceutical filler (diluent) material, including but not limited to sucrose, dextrose, lactose, microcrystalline cellulose, xylitol, fructose, sorbitol, mixtures thereof and the like. Also, an effective amount of any generally accepted pharmaceutical lubricant, including the calcium or magnesium soaps may be added to the above-mentioned ingredients of the excipient prior to compression of the tablet core ingredients. Most preferred is magnesium stearate in an amount of about 0.5-3% by weight of the solid dosage form.

Tablets overcoated with a sufficient amount of aqueous dispersions of ethylcellulose to achieve a controlled release formulation pursuant to the present may be prepared and cured in similar fashion as explained above with regard to the preparation of beads. One skilled in the art will recognize that necessary curing conditions with regard to the particular elevated temperature, elevated humidity and time ranges necessary to obtain a stabilized product, will depend upon the particular formulation.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The following examples illustrate various aspects of the present invention. They are not to be construed to limit the claims in any manner whatsoever.

EXAMPLE 1

Hydromorphone beads were prepared by dissolving hydromorphone HCl in water, adding Opadry® Y-5-1442, light pink (a product commercially available from Coloron, West Point, Pennsylvania, which contains hydroxypropyl methylcellulose, hydroxypropyl cellulose, titanium dioxide, polyethylene glycol and D&C Red No. 30 Aluminum Lake), 20% w/w, and mixing for about 1 hour, and then spraying onto nu pariel 18/20 beads using a Wurster insert. The resultant coated beads were then overcoated with Opadry® Y-5-1442 light pink (15% w/w). The resultant preparation had the formula set forth in Table 1 below:

TABLE 1

Ingredient	Percent	Amt/Unit
Hydromorphone HCl	4.75%	4 mg
Nu Pariel 18/20	87.9%	74 mg
Opadry® Lt. Pink Y-5-1442	2.4%	2 mg
Opadry® " (overcoat)	5.0%	4.2mg
	100.0%	84.2mg

The hydromorphone, HPMC protected beads were then overcoated with 15% w/w Aquacoat® (including triethyl citrate), and then overcoated with Opadry® Light Pink 5% w/w after curing (see Table 2). The beads cured at high humidity were dried in a fluid bed before the final overcoat.

TABLE 2

Composition After Coating	
Ingredient	Percent
Hydromorphone beads	80.57%
Aquacoat® ECD 30	12.06%
Triethyl citrate	2.39%
Opadry® Lt. Pink Y-5-1442 (Overcoat)	4.98%
	100.0%

The product was then divided into four portions. In Example 1, the coated beads were placed in a 30 cc amber glass vial and cured in an oven for 72 hours at 60 °C/85% relative humidity. In Comparative Example 1A, the coated beads were cured for 24 hours at 60 °C under dry conditions. In Comparative Example 1B, the coated beads were cured for 72 hours at 60 °C under dry conditions. In Comparative Example 1C, the coated beads were cured for 24 hours at 60 °C at 85% relative humidity.

All products cured at the four above-mentioned different conditions were then tested for stability under the following conditions: Room Temperature; 37 °C dry; 37 °C/80% Relative Humidity (RH); 50 °C dry; 60 °C dry; and 60 °C/85% RH.

The relative humidity in a water-filled desiccator in a 60 °C oven was determined as follows. First, about 500 grams of purified water is poured into a plastic desiccator and the metal guard inserted. A hygrometer/temperature indicator is placed on top of the guard and the desiccator covered and placed in the 60 °C oven for 24 hours. After 24 hours the relative humidity in the desiccator was 85% while the temperature was still 60 °C. On placing the hygrometer alone in the 60 °C oven for 24 hours, the relative humidity was 9% at 60 °C.

The dissolution tests were carried out via the USP Basket Method, 37 °C, 100 RPM, first hour 700 ml gastric fluid at pH 1.2, then changed to 900 ml at 7.5. In each instance, the dissolution was conducted by placing an open capsule containing the specified amount of cured beads (8mg hydromorphone HCl, 209mg beads ± 10%) into a vessel.

It was observed that the dissolution of Example 1 did not change under these accelerated conditions, except that changes were seen with respect to the extreme conditions of 60 °C/85% RH. The results for Example 1 are set forth in Tables 3-8 below, :

TABLE 3

ROOM TEMPERATURE								
Time (wks)	Hydromorphone HCl (Amount)	Dissolution						
		1	2	3	8	12	18	24
Initial	8.14 mg	0	4.6	29.5	52.6	64.7	76.6	82.8
1	7.95 mg	0	5.1	30.3	55.0	67.4	79.8	88.9
4	7.80 mg	1.3	8.2	33.5	57.4	70.0	82.8	90.9
8	7.78 mg	0.7	6.0	30.5	54.0	66.4	78.0	88.2

TABLE 4

37 ° C DRY								
Time (wks)	Hydromorphone HCl (Amount)	Dissolution						
		1	2	3	8	12	18	24
Initial	8.14 mg	0	4.6	29.5	52.6	64.7	76.6	82.8
1	7.96 mg	0	6.0	30.8	55.3	68.0	81.6	89.7
4	7.91 mg	2	8.1	33.2	56.6	70.2	82.0	91.3
8	7.73 mg	1	5.8	31.3	57.5	64.6	82.7	91.6

TABLE 5

37 ° C/80%RH								
Time (wks)	Hydromorphone HCl (Amount)	Dissolution						
		1	2	3	8	12	18	24
Initial	8.19 mg	0	4.6	29.5	52.6	64.7	76.6	82.8
1	7.85 mg	0	5.6	31.0	55.1	68.5	80.3	89.1
4	8.16 mg	2.4	7.6	32.3	52.8	64.4	75.4	82.7
8	8.22 mg	2.9	7.9	33.5	53.3	64.5	73.6	81.3

TABLE 6

50 ° C (dry)								
Time (wks)	Hydromorphone HCl (Amount)	Dissolution						
		1	2	3	8	12	18	24
Initial	8.14 mg	0	4.6	29.5	52.6	64.7	76.6	82.8
1	8.14 mg	0	6.3	32.7	56.3	68.3	80.8	89
4	7.81 mg	2.3	10	37.0	59.6	72.0	84.5	92
8	7.74 mg	2	10.4	35.8	59.2	71.3	82.3	90.5

TABLE 7

60 ° C (dry)								
Time (wks)	Hydromorphone HCl (Amount)	Dissolution						
		1	2	3	8	12	18	24
Initial	8.14 mg	0	4.6	29.5	52.6	64.7	76.6	82.8
1	8.13 mg	0	6.7	34.6	57.8	70.3	82.1	90.5
4	8.30 mg	2.7	10.6	36.6	56.8	68.7	80.4	85.6
8	7.94 mg	3.6	11.9	37.4	58.4	71.1	80.6	89.3

TABLE 8

60 ° C/100% RH								
Time (wks)	Hydromorphone HCl (Amount)	Dissolution						
		1	2	3	8	12	18	24
Initial	8.14 mg	0	4.6	29.5	52.6	64.7	76.6	82.8
1	7.26 mg	6.1	9.9	23.4	42.4	53.3	63.1	72.5
4	6.64 mg	19	23.7	32.5	41.4	46.7	53.0	51.7
8	5.38 mg	25.1	28.4	33.2	40.0	44.1	47.7	52.0

In contrast, the dissolution profiles of Comparative Examples 1A, 1B and 1C continued to slow down (e.g., cure) at all accelerated conditions. The results are set forth in Tables 9, 10 and 11, respectively.

TABLE 9 - Comparative Example 1A

Conditions/ Time	Hydromorphone HCl (Amount)	Dissolution							
		1	2	3	8	12	18	24	
Initial	9.03 mg	17.8	43.6	63.6	78.8	86.7	94.7	94.2	
Room Temp.									
8 wks	8.79 mg	18.4	35.9	58.2	76.3	88.7	97	*	
37°C (dry)									
8 wks	8.50 mg	14	36.5	59.1	81.1	91.4	99.4	*	
37°C/80%RH									
8 wks	8.15 mg	6.6	23.6	41.2	60.7	72.3	83.1	*	
50°C (dry)									
8 wks	8.45 mg	17.3	36	56.1	78.1	89.1	97.1	102.6	
60°C (dry)									
8 wks	8.65 mg	7.3	28.5	48.9	64.4	82	92.3	99.1	
60°C/100%RH									
8 wks	5.81 mg	17.5	22.6	28.8	36.5	41.7	46.5	50.3	

TABLE 10 - Comparative Example 1B

Conditions/ Time	Hydromorphone HCl (Amount)	Dissolution							
		1	2	3	8	12	18	24	
Initial	8.82 mg	4.7	35.5	58.3	75.6	87.3	96.0	98.2	
Room Temp.									
8 wks	8.29 mg	8.7	34.6	59.3	80.8	92.1	99.2	105.7	
37°C (dry)									
8 wks	8.34 mg	8.3	36.1	55.9	77.4	87.3	97.8	103.1	
37°C/80%RH									
8 wks	8.86 mg	4.9	25.4	43.6	61.7	70	80	87.2	
50°C (dry)									
8 wks	8.71 mg	10.8	35.4	55.9	77.2	88.9	99.5	103.2	
60°C (dry)									
8 wks	8.30 mg	5.3	32	54.1	76.6	87.2	99.8	105.5	
60°C/100%RH									
8 wks	6.22 mg	16.3	21.2	27.4	35.9	40.5	46.2	49.4	

TABLE 11 - Comparative Example 1C

Conditions/ Time	Hydromorphone HCl (Amount)	Dissolution							
		1	2	3	8	12	18	24	
Initial	8.71 mg	0.7	15.3	41.9	60.7	71.2	82.4	86.7	
Room Temp.									
8 wks	8.40 mg	1	14.2	39.8	58.8	69.1	79.1	87.2	
37°C (dry)									
8 wks	8.84 mg	2.7	14.5	40.5	60.4	71	81.3	89.8	
37°C/80%RH									
8 wks	8.78 mg	2.5	12.4	37.8	54.6	63.8	73.3	*	
50°C (dry)									
8 wks	8.71 mg	3.2	17.5	42.3	61.1	70.8	81	87.9	
60°C (dry)									
8 wks	8.57 mg	2.9	18.2	43.4	62.5	73.6	84.3	*	
60°C/100%RH									
8 wks	6.10 mg	15.7	20.3	26.4	33.8	38.3	43.1	46.7	

Figure 1 is a graphical representation of the dissolution results obtained with Example 1, comparing the initial dissolution profile with the dissolution profile after 8 weeks storage at 37 °C/80%RH.

Figure 2 is a graphical representation of the dissolution profile of Comparative Example 1A, comparing the initial dissolution profile with the dissolution profile after 8 weeks storage at 37 °C/80%RH.

Figure 3 is a graphical representation of the dissolution profile of Comparative Example 1B, comparing the initial dissolution profile with the dissolution profile after 8 weeks storage at 37 °C/80%RH.

Figure 4 is a graphical representation of the dissolution profile of Comparative Example 1C, comparing the initial dissolution profile with the dissolution profile after 8 weeks storage at 37 °C/80%RH.

Comparing the results depicted in Figure 1 (Example 1) with the results depicted in Figures 2-4 (the comparative examples), it is readily apparent that only in Example 1 were the initial and 8 week dissolution profiles substantially identical under storage conditions of 37 °C/80%RH.

Figure 5 is a graphical representation of the dissolution profiles of Example 1, comparing the initial dissolution profile with the dissolution profiles obtained after 8 weeks storage under various conditions (room temperature; 37 °C/80%RH; and 60 °C dry). The dissolution profiles of Example 1 after 8 weeks under these various conditions is seen to be substantially identical.

Finally, Figure 6 is a graphical representation of the initial dissolution profiles obtained after various curing conditions (curing of 2hrs at 60 °C dry (the prior art); 72hrs at 60 °C/85%RH (Comparative Example 1); 24hrs at 60 °C/85%RH (Comparative Example 1A); 24hrs at 60 °C dry (Comparative Example 1B); and 72hrs at 60 °C dry (Comparative Example 1C)).

EXAMPLE 2 - Curing at 60 °C Dry Heat - Longer Drying

In Example 2, hydromorphone HCl beads were prepared in accordance with Example 1 in order to determine if the stabilized initial dissolution achieved after curing at 60 °C/85%RH could instead be achieved by a longer drying period without humidity. After coating with Aquacoat®, a further overcoat of Opadry® Y-5-1442, light pink is applied to the beads. The coated product had the composition set forth in Table 12 below:

TABLE 12

Composition After Coating		
Ingredient	Percent	Amt/Unit
Hydromorphone beads	80.57%	84.2mg
Aquacoat® ECD 30	12.06%	12.6mg
Triethyl citrate	2.39%	2.5mg
Opadry® Lt. Pink (Overcoat)	4.98%	5.2mg
	100.0%	99.3mg

The Aquacoat® coated hydromorphone HCl beads were then cured in a 60 °C dry oven, and stored at 60 °C dry heat. The cured beads were placed in open gelatin capsules containing the specified amount of cured beads (about 8mg hydromorphone HCl), and dissolution studies were then conducted in the manner set forth in Example 1 on three samples at the following time points: initial, 1 day, 2 days, 7 days, and 21 days in order to determine the stability of the dissolution profile. Dissolution studies were conducted as detailed above on the three samples. The mean results are set forth in Table 13 below:

TABLE 13

Dissolution (Time)								
Time (Days)	Wt (mg)	1 hr	2 hr	4 hr	8 hr	12 hrs	18 hrs	24 hrs
Initial	196.7	15.6	43.8	68.7	89.9	101.0	109.2	113.8
1	196.3	3.7	37.5	63.5	84.9	97.5	107.2	112.3
2	196.3	4.8	37.0	62.9	84.8	95.1	104.7	111.8
7	197.3	13.5	37.8	63.3	84.9	98.8	108.6	115.9
21	197.3	17.4	36.5	58.4	77.9	88.9	98.2	103.1

From the results set forth in Table 13 above, it is apparent that a profound slow down in release rate of the samples of Example 2 occurred, as compared with the high temperature/high humidity condition of Example 1. In other words, an endpoint was not reached at which the dissolution profile gets down to the base level of Example 1.

Example 3 - Increased Mixing Time

In Example 3, another attempt to stabilize Aquacoat® coated hydromorphone HCl beads using the premise that high temperature is not enough to insure complete coalescence of the ethylcellulose film. Normal time of mixing (and bonding) plasticizer and Aquacoat® is recommended by FMC to be 30 minutes. In Example 3, the contact time of the plasticizer (triethyl citrate) with the ethylcellulose polymer dispersion (Aquacoat®) was increased to 24 hours.

The coated beads were prepared in accordance with Example 1 and then placed in a 30 cc amber glass vial and cured in a 60 °C dry oven. Dissolution studies were then conducted on three samples at the following time points: 1 day, 2 days, 7 days and 11 days. Mean results are set forth in Table 14 below:

TABLE 14

Dissolution (Time)								
Time (Days)	Wt(mg)	1 hr	2 hr	4 hr	8 hr	12 hrs	18 hrs	24 hrs
1	210.7	27.7	53.3	77.3	95.7	103.4	108.2	110.4
2	209.7	25.9	50.3	74.3	94.2	101.9	106.4	110.2
7	209.7	24.8	48.3	73.1	95.2	102.7	108.5	112.6
11	210.3	24.0	45.4	70.5	94.9	103.9	113.3	115.9

From the results set forth in Table 14 above, it is apparent that a profound slow down in release rate of the samples of Example 2 occurred, as compared with the high temperature/high humidity condition of Example 1. In other words, an endpoint was not reached at which the dissolution profile gets down to the base level of Example 1.

EXAMPLE 4 - Recommended Curing (Prior Art)

Hydromorphone beads were prepared by dissolving hydromorphone HCl in water, adding Opadry®, and mixing for about 1 hour, and then spraying onto nu pariel 18/20 beads using a Wurster insert. The resultant coated beads were then overcoated with Opadry® Y-5-1442 light pink (15% w/w). The beads were then overcoated with a aqueous dispersion of Aquacoat® to a 15% weight gain according to Table 15 below:

TABLE 15

Ingredient	Percent (wt)	Amt/Unit
Hydromorphone beads	84.7	80 mg
Aquacoat® CD 30	12.7	12 mg
Citroflex®2A (Triethylcitrate)	2.5	2.4 mg
	99.9	94.4 mg

After the resin was applied to the beads, the beads were cured in a fluid bed for about 2 hours at 60 °C, as suggested in the literature and as recommended by FMC, since it is above the Tg for Aquacoat® plasticized with triethyl citrate at 20% level of solids.

The cured beads were then stored at room temperature, with dissolution studies being conducted initially and at 3 months. Samples were also stored at 37 °C/80% RH. The mean results are provided in Table 16:

TABLE 16

<u>Time</u>	<u>Mean wt</u>	<u>1 hr</u>	<u>2 hr</u>	<u>4 hr</u>	<u>8 hr</u>	<u>12 hrs</u>	<u>18 hrs</u>	<u>24 hrs</u>
Initial	283.2	30.4	44	70.2	89.1	97.0	101.3	102.1
3 mos	282.3	36.2	57.8	76.9	89.0	93.4	96.6	98.5
<u>37 °C/80% RH</u>								
1 mo	288.4	0.5	26.7	50.5	69.6	80.7	90.7	97.0
2 mos	287.3	0.6	25.1	50.7	70.3	81.6	92.2	98.8
3 mos	293.7	1.2	23.7	48.6	65.6	74.5	80.2	83.5

From the results provided in Table 16 above, it can be seen that the dissolution profile of the samples stored at room temperature were acceptable. However, the dissolution of the samples slowed dramatically when stored at 37 °C/80% RH.

Samples from the batch of Example 4 were repackaged, stored and thereafter subjected to heat under dry conditions at 37 °C and moisture (37 °C/80% RH). The dissolution results are provided in Table 17 below:

TABLE 17

<u>Time</u>	<u>Mean wt</u>	<u>1 hr</u>	<u>2 hr</u>	<u>4 hr</u>	<u>8 hr</u>	<u>12 hrs</u>	<u>18 hrs</u>	<u>24 hrs</u>
Initial	283.2	30.4	49.0	70.3	89.1	97.0	101.3	102.1
<u>37 ° Dry</u>								
2 wks	283.2	25.0	44.4	65.0	84.5	92.9	100.7	104.4
4 wks	280.7	21.5	28.0	63.5	84.3	95.6	-	-
<u>37 °C/80% RH</u>								
2 wks	283.2	16.6	39.1	60.5	80.1	89.8	99.8	103.4
4 wks	281.3	4.6	26.6	53.7	71.4	82.1	-	-

From the results set forth above, it is apparent that under dry conditions at 37 °C, the dissolution of Example 4 did not come to the same endpoint as at 37 °C/80% RH. Thus, the combination of both moisture and heat was required to complete the curing.

EXAMPLES 5-7

To test the effectiveness of high temperature (60 °C), high humidity curing as an effective process of stabilizing plasticized ethylcellulose controlled release films, Examples 5-7 were manufactured at different levels of Aquacoat® load.

In each of Examples 5-7, hydromorphone beads were made according to Example 1. Thereafter, overcoatings of 5% w/w, 10% w/w, and 15% w/w were applied to Examples 5-7 respectively, according to the formulas set forth in Tables 18-20:

TABLE 18

Composition of Ex. 5 After Coating		
Ingredient	Percent	Amt/Unit
Hydromorphone beads	84.2%	84.2mg
Aquacoat® ECD 30	4.7%	4.2mg
Triethyl citrate	0.9%	0.84mg
	100%	89.24mg

TABLE 19

Composition of Ex. 6 After Coating		
Ingredient	Percent	Amt/Unit
Hydromorphone beads	89.3%	84.2mg
Aquacoat® ECD 30	8.9%	8.4mg
Triethyl citrate	1.8%	1.7mg
	100%	94.3mg

TABLE 20

Composition of Ex. 7 After Coating		
Ingredient	Percent	Amt/Unit
Hydromorphone beads	84.8%	84.2mg
Aquacoat® ECD 30	12.7%	12.6mg
Triethyl citrate	0.9%	2.5mg
	100%	99.3mg

All three batches were cured in water loaded desiccators in a 60 °C oven. These batches were placed on screen trays in these desiccators after the Aquacoat® film was applied to the HPMC overcoated hydromorphone HCl bead. The desiccators containing the Aquacoat®-coated beads were then placed in a 60 °C oven for 72 hours. Thereafter, the batches were removed from the ovens. The beads appeared moist and therefore were dried in a lab line fluid bed dryer for one hour. They were then overcoated with 5% w/w Opadry® Y-5-1442 light pink in a Wurster insert.

Stability studies on Examples 5-7 show the initial dissolutions to be the same as dissolutions done on samples placed at 37 °C/80% RH conditions. The results are provided in Tables 21-23 below:

EP 0 548 448 A1

TABLE 21

Dissolution (Time) - 5% Aquacoat®								
Time (Days)	Wt (mg)	1 hr	2 hr	4 hr	8 hr	12 hrs	18 hrs	24 hrs
Initial	190	39.8	57.4	73.0	88.0	93.8	98.0	95.6
28	191	33.4	54.6	71.9	84.2	89.8	94.6	96.4

TABLE 22

Dissolution (Time) - 10% Aquacoat®								
Time (Days)	Wt (mg)	1 hr	2 hr	4 hr	8 hr	12 hrs	18 hrs	24 hrs
Initial	200.3	7.5	27.9	48.5	68.1	76.2	90.3	88.9
28	210	9.9	32.4	52.6	67.8	77.9	85.9	90.9

TABLE 23

Dissolution (Time) - 15% Aquacoat®								
Time (Days)	Wt (mg)	1 hr	2 hr	4 hr	8 hr	12 hrs	18 hrs	24 hrs
Initial	210	5.4	13.9	38.0	57.8	68.4	78.6	81.3
28	207.3	9.5	23.8	43.4	58.8	67.8	77.0	81.3

EXAMPLE 8

In Example 8, Hydromorphone beads overcoated with 10% of the Aquacoat® are prepared in accordance with Example 6. The hydromorphone beads of Example 8 have the following formula set forth in Table 24 below:

TABLE 24

Ingredient	Percent	Amt/Unit
Hydromorphone beads	89.3%	84.2 mg
Aquacoat® ECD30	8.9%	8.4 mg
Triethyl citrate	1.8%	1.7 mg
	100%	94.3 mg

To test the effectiveness of curing at a lower relative humidity compared to Example 6, the above beads were cured for 72 hours at 60 °C at 60% relative humidity (rather than 85%RH). Similar initial results were obtained for Example 8 as compared to Example 6, thus indicating that the curing step can also be completed at a lower relative humidity. The results are set forth in Table 25 below:

TABLE 25

Dissolution (Time) - 10% Aquacoat®							
Example	1 hr	2 hr	4 hr	8 hr	12 hr	18 hr	24 hr
Ex. 8	7.5	27.9	48.5	68.1	76.2	90.3	88.9
Ex. 6	1.1	18.9	45.0	65.0	76.0	85.8	91.5

EXAMPLES 9-10

Hydromorphone HCl beads were prepared made by spraying a suspension of Hydromorphone HCl and Opadry® Y-5-1442 light pink (20%w/w) onto nu-pariel 18/20 beads, in accordance with the method set forth in Example 1. These beads were then further coated with Opadry® Y-5-1442 light pink (15% w/w). These beads were then further coated with the Surelease® at a level of 10% weight gain. The formula of the coated bead is set forth in Table 26:

TABLE 26

Ingredient	mg/dose	Percent
Hydromorphone HCl	4.0 mg	4.32%
NuPariel beads 18/20	74.0 mg	79.91%
Opadry light pink	6.2 mg	6.70%
Surelease	8.4 mg	9.07%
	<u>92.6 mg</u>	<u>100%</u>

The batch was then divided into two portions. Example 9 was cured at 60°C/85% RH for 3 days (72 hours), and then dried in a fluid bed dryer for 30 minutes at 60°C to dry off the excess moisture. These beads were then overcoated with 5% Opadry light pink. Example 10 was left uncured.

Both Examples 9 and 10 were then filled into hard gelatin capsules at a strength of 4 mg hydromorphone per capsule and stored for 3 months at 37°C/80% RH. Dissolution studies were conducted (pursuant to the method set forth for Example 1) initially for both Examples 9 and 10 and again after the 3 month storage at 37°C/85% RH. The results are set forth in Tables 27 and 28 below:

TABLE 27

Example 9		
Time	Initial	3 Months at 37°C/80% RH
1	4.7	6.5
4	42.3	56.0
8	64.9	75.0
12	77.2	83.19

TABLE 28

Example 10		
Time	Initial	3 Months at 37° C/80% RH
1	1.6	4.5
4	12.0	61.9
8	47.8	79.0
12	66.7	87.7

The results indicate that despite the expected differences in initial release rates caused by the use of a different aqueous dispersion of ethylcellulose (Surelease® as compared to Aquacoat®), the curing step as described above for Example 9 still significantly stabilized the product in comparison to the uncured product of Example 10. The relatively faster controlled release rate of the Examples using Aquacoat® as compared to Surelease® may be due to the lesser degree of plasticization during the preparation of the coating formulation. However, products using either coating may be modified to obtain satisfactory results.

EXAMPLE 11

The following example illustrates the stabilization of morphine beads in accordance with the present invention.

A suspension of morphine sulphate and HPMC (Opadry® Clear Y-5-7095) was applied onto 18/20 mesh Nu-pariel beads in a fluid bed granulator with a Wurster column insert, at 60°C. A HPMC purple color suspension (Opadry® Lavender YS-1-4729) was then applied as an overcoat at the same temperature. The beads were then overcoated to a 5% weight gain with Aquacoat® and triethyl citrate as a plasticizer at 60°C inlet. The beads were then cured in an oven at 60°C/100% relative humidity for three days. The beads were then dried in the fluid bed granulator at 60°C, and an overcoat of HPMC with a purple color was then applied using the Wurster column.

The beads were then filled into hard gelatin capsules at a strength of 30 mg morphine sulphate per capsule. The final formula, set forth in Table 29 thus became:

TABLE 29

Ingredient	mg/capsule	Percent
Morphine sulphate 5H ₂ O	30.0	8.51%
Nu-pariel beads 18/20	255.0	72.36%
Opadry® Clear Y-5-7095	15.0	4.26%
Opadry® Lavender YS-1-4729	15.8	4.48%
Aquacoat® ECD30 (solids)	15.8	4.48%
Triethyl citrate	3.2	0.91%
Opadry Lavender Y-S-1-4729	17.6	4.99%
	352.4	100%

An initial dissolution of the capsules was conducted using the USP paddle method at 100 rpm in 900 ml of water, and again after storage at 37°C/80% relative humidity, and at 60°C dry for one month. It was observed that a stable product was made. The results are set forth in Table 30:

TABLE 30

Percent Morphine Dissolved			
Time Hrs	Initial	37 ° C/80% RH after 1 Mo	60 ° C after 1 Mo
1	15.7	16.6	15.3
4	53.0	51.4	54.9
8	84.4	83.3	90.4
12	96.5	94.4	96.9

EXAMPLE 12

A second experiment was conducted with morphine as described in Example 11; however, the retardant Aquacoat® layer was applied to a 15% weight gain to develop a slower releasing morphine product. The final formulation is set forth in Table 31:

TABLE 31

Ingredient	Mg/capsule	Percent
Morphine sulphate 5H ₂ O	30.0	7.65%
Nu-pariel beads 18/20	255.0	65.0%
Opadry® Clear Y-5-7095	15.0	3.82%
Opadry® Lavender YS-1-4729	15.8	4.03%
Aquacoat® ECD30 (solids)	47.4	12.08%
Triethyl citrate	9.5	2.42%
Opadry® Lavender Y-S-1-4729	19.6	5.00%
	392.3	100%

An initial dissolution of the 30 mg morphine sulphate capsules was conducted as described in Example 10 and again after storage at 37 ° C/100% relative humidity and 60 ° C dry for one month. It was again observed that a stable product was made. The results are set forth in Table 32 below:

TABLE 32

Percent Morphine Dissolved			
Time Hrs	Initial	37 ° C/80%RH After 1 Mo	60 ° C After 1 Mo
1	0	3.1	0
4	18.1	19.4	17.8
8	49.2	49.4	45.7
12	66.3	68.2	65.9

EXAMPLES 13-14

In Example 13, the applicability of another medicament, theophylline, having very different physical properties compared to hydromorphone is demonstrated.

Theophylline hydrous and colloidal silicon dioxide were first mixed together in a high shear mixer, then sieved using a Jet sieve to enhance flowability. Using a fluid bed granulator equipped with a rotor processor, sugar spheres were layered with the theophylline/colloidal silicon dioxide mixture using a PVP (C-30) solution. Layering was continued until an approximately 78% load was obtained.

The formula of the 400mg theophylline beads when filled into capsules is set forth in Table 33 as follows:

TABLE 33

	Mg/unit capsules
Theophylline hydrous (equivalent to 400 mg anhydrous theophylline)	440.0
Colloidal silicon dioxide	0.4
Sugar spheres 30/35 mesh	110.0
PVP (C-30)	13.5
	563.9

These spheres were then overcoated with a dibutylsebecate plasticized Aquacoat® ECD 30 retardant to a 5% weight gain in the Wurster column in a fluid bed granulator. A portion of the spheres was not cured, and another portion was stored at 60 °C and 100% relative humidity for 72 hours. The following results set forth in Table 34 were obtained:

TABLE 34

	1 hr	2 hr	3 hr	4 hr	6 hr	8 hr	24 hr
Initial(uncured)	9.0	92.8	94.6	95.4	97.8	98.0	100.0
72 hours at 60 °C/85% RH	3.2	5.3	7.0	7.9	11.0	14.1	35.8

From the above, it was determined that theophylline spheroids coated with Aquacoat® also are not stable and need to be cured. After storage at 72 hours at 60 °C and 85% relative humidity, a dramatic drop in dissolution rate occurred; however, such conditions may, in some instances, represent "ideal" curing conditions to form a stable product. In view of this goal, the dissolution data after 72 hours at 60 °C/85%RH provides too slow a dissolution profile for theophylline.

Therefore, Example 14 was prepared in order to attempt to improve the dissolution profile of the formulation via incorporation of this new curing step, and the coating was altered in order to increase the dissolution rate to 100% theophylline dissolved in 12 hours.

Example 14 was prepared as follows. Theophylline powder layered beads were made as described in Example 13 and were then overcoated with a plasticized Aquacoat® ECD 30 retardant, which, and for this example, included 10% HPMC (hydroxypropyl methyl cellulose). This was done so that the release of theophylline would be faster than Example 13. The inclusion of HPMC to speed up dissolution is known in the prior art. The retardant layer was also coated to a 6% weight gain in the Wurster column of the fluid bed granulator.

The coated beads were then cured for 72 hours at 60 °C/85% relative humidity. A dissolution study was conducted initially, and once again after the beads were stored at 37 °C/80% relative humidity for three months. It was observed that the stability of the dissolution of the theophylline from the formulation of Example 14 improved dramatically compared to Example 13. It was further observed that by inclusion of HPMC in the retardant layer in the proportions of Aquacoat® ECD 30 (solids):HPMC of 9:1, coated to a 6% weight gain, the dissolution rate of the formulation was increased to 100% theophylline dissolved in 12 hours. The results are set forth in detail in Table 35 below:

TABLE 35

	1 hr	2 hr	4 hr	8 hr	12 hr
Cured Initial	17	38	68	97	100
Storage at 37 °C/80%RH for 3 months	13	31	60	94	100

The examples provided above are not meant to be exclusive. Many other variations of the present invention would be obvious to those skilled in the art.

For example, although the present invention has been described with respect to the most preferred hydrophobic polymer, ethylcellulose, it is contemplated that other hydrophobic polymers, such as other cellulose derivatives, may also be useful in conjunction with the present invention. Such other hydrophobic polymers are considered to be within the scope of the appended claims.


Likewise, as previously explained, one skilled in the art will recognize that necessary curing conditions may be change somewhat depending upon the particular formulation (including the amount of overcoating, the properties of the therapeutically active agent, etc.), such that a stabilized product is obtained via a modified range with regard to temperature, humidity and time. Such variations are contemplated to be within the scope of the appended claims.


Claims


1. A method for obtaining a stabilized controlled release formulation comprising a substrate coated with an aqueous dispersion of a hydrophobic polymer, comprising
 - preparing an aqueous dispersion of plasticized ethylcellulose,
 - preparing a solid substrate comprising a therapeutically active agent,
 - overcoating said substrate with a sufficient amount of said aqueous dispersion of ethylcellulose to obtain a predetermined controlled release of said therapeutically active agent when said coated substrate is exposed to aqueous solutions,
 - curing said coated substrate under stressed conditions by subjecting said coated substrate to a temperature greater than the glass transition temperature of the aqueous dispersion of ethylcellulose and at a greater than ambient relative humidity and continuing the curing until an endpoint is reached at which said substrate attains a dissolution profile which is substantially unaffected by further exposure to storage conditions of elevated temperature and/or humidity.
2. The method of claim 1, further comprising determining the endpoint for the formulation by exposing the formulation which is uncured or substantially uncured to stressed storage conditions and obtaining dissolution profiles for the formulation until the dissolution profiles of the formulation are substantially stabilized.
3. The method of claim 2, further comprising modifying the formulation to obtain a desired dissolution profile of said therapeutically active agent based on said end point.
4. The method of claim 1, further comprising preparing said substrate for oral administration by coating said therapeutically active agent onto the surface of pharmaceutically acceptable beads, and preparing an oral dosage form by placing a sufficient quantity of cured coated beads into a capsule.
5. The method of claim 1, further comprising preparing said substrate for oral administration by incorporating said therapeutically active agent into a tablet.
6. The method of claim 1, further comprising overcoating said substrate comprising said therapeutically active agent with a barrier agent prior to overcoating with said aqueous dispersion of ethylcellulose.
7. The method of claim 6, wherein said barrier agent comprises hydroxypropyl methylcellulose.
8. The method of claim 1, wherein said coated particles are cured from about 60% to about 100% relative humidity at an elevated temperature above the glass transition temperature of the coating for about 48 to about 72 hours, until the endpoint is reached.
9. The method of claim 1, wherein said therapeutically active agent is selected from the group consisting of antihistamines, analgesics, anti-inflammatory agents, gastro-intestinals, anti-emetics, anti-epileptics, vasodilators, anti-tussive agents, expectorants, anti-asthmatics, anti-spasmodics, hormones, diuretics, anti-hypotensives, bronchodilators, anti-inflammatory steroids, antibiotics, antihemorrhoidals, hypnotics, psychotropics, antidiarrheals, mucolytics, sedatives, decongestants, laxatives, antacids, vitamins, and stimulants.
10. The method of claim 1, wherein said therapeutically active agent is selected from the group consisting of hydromorphone, oxycodone, dihydrocodeine, codeine, dihydromorphine, morphine, buprenorphine, salts of any of the foregoing, and mixtures of any of the foregoing.
11. The method of claim 1, wherein said therapeutically active agent is theophylline.

12. The product prepared according to the method of claim 1.
13. The product prepared according to the method of claim 4.
- 5 14. The product prepared according to the method of claim 5.
15. A stabilized solid controlled release dosage form comprising a substrate comprising a therapeutically active agent, said substrate overcoated with an aqueous dispersion of plasticized ethylcellulose and cured at a temperature greater than the glass transition temperature of the aqueous dispersion of the plasticized ethylcellulose and at a relative humidity greater than ambient conditions such that the coated substrate attains a stabilized dissolution profile substantially unaffected by exposure to storage conditions of elevated temperature and/or elevated relative humidity.
- 10 16. The stabilized solid controlled release dosage form of claim 15, wherein said therapeutically active agent is overcoated with said aqueous dispersion of ethylcellulose to a weight gain level from about 5 to about 15 percent.
17. The stabilized solid controlled release dosage form of claim 16, further comprising an inert pharmaceutically acceptable bead onto which said therapeutically active agent is coated.
- 20 18. The stabilized solid controlled release dosage form of claim 17, wherein a plurality of said coated, cured beads are placed in a capsule in an amount sufficient to provide an effective controlled release dose when contacted by an aqueous solution.
- 25 19. The stabilized solid controlled release dosage form of claim 15, wherein said therapeutically active agent is selected from the group consisting of antihistamines, analgesics, anti-inflammatory agents, gastro-intestinals, anti-emetics, anti-epileptics, vasodilators, anti-tussive agents, expectorants, anti-asthmatics, anti-spasmodics, hormones, diuretics, anti-hypotensives, bronchodilators, anti-inflammatory steroids, antibiotics, antihemorrhoidals, hypnotics, psychotropics, antidiarrheals, mucolytics, sedatives, decongestants, laxatives, antacids, vitamins, and stimulants.
- 30 20. The stabilized solid controlled release dosage form of claim 15, wherein said therapeutically active agent is selected from the group consisting of hydromorphone, oxycodone, dihydrocodeine, codeine, dihydromorphine, morphine, buprenorphine, salts of any of the foregoing, and mixtures of any of the foregoing.
- 35 21. The stabilized solid controlled release dosage form of claim 15, wherein said therapeutically active agent is theophylline.
- 40 22. A stabilized controlled release solid dosage form for oral administration, comprising a plurality of suitable inert pharmaceutically acceptable beads coated with a therapeutically active agent, and an ethylcellulose overcoat of a thickness suitable to obtain a controlled release of said therapeutically active agent when said solid dosage form is exposed to aqueous solutions, said ethylcellulose overcoat being derived from an aqueous dispersion of ethylcellulose with an effective amount of a suitable plasticizing agent,
45 said ethylcellulose coated solid dosage form being cured under stress conditions of elevated temperature and humidity to attain a finished product which has a dissolution profile which is substantially unaffected by exposure to storage conditions of elevated temperature and/or humidity.
- 50 23. The stabilized controlled release solid dosage form of claim 22 which is cured at a temperature above the glass transition temperature of the plasticized ethylcellulose coating and at a relative humidity from about 60 about 100 percent for about 48 to about 72 hours.
- 55 24. The stabilized solid controlled release dosage form of claim 22, wherein a plurality of said coated, cured beads are placed in a capsule in an amount sufficient to provide an effective controlled release dose when contacted by an aqueous solution.

25. The stabilized solid controlled release dosage form of claim 22, wherein said therapeutically active agent is selected from the group consisting of antihistamines, analgesics, anti-inflammatory agents, gastro-intestinals, anti-emetics, anti-epileptics, vasodilators, anti-tussive agents, expectorants, anti-asthmatics, anti-spasmodics, hormones, diuretics, anti-hypotensives, bronchodilators, anti-inflammatory steroids, antibiotics, antihemorrhoidals, hypnotics, psychotropics, antidiarrheals, mucolytics, sedatives, decongestants, laxatives, antacids, vitamins, and stimulants.
5
26. The stabilized solid controlled release dosage form of claim 22, wherein said therapeutically active agent is selected from the group consisting of hydromorphone, oxycodone, dihydrocodeine, codeine, dihydromorphine, morphine, buprenorphine, salts of any of the foregoing, and mixtures of any of the foregoing.
10
27. The stabilized solid controlled release dosage form of claim 22, wherein said therapeutically active agent is theophylline.
15
28. A solid dosage form comprising a core comprising a therapeutically active agent and an overcoating derived from an aqueous dispersion of ethylcellulose in an amount sufficient to obtain a controlled release of said therapeutically active agent when said dosage form is exposed to aqueous solutions, said solid dosage form being cured after said overcoating is applied such that the release of said therapeutically active agent is substantially unaffected by exposure to elevated temperature and/or humidity.
20
29. A method of stabilizing a substrate comprising a therapeutically active agent having a overcoating derived from an aqueous dispersion of plasticized ethylcellulose in an amount sufficient to obtain a controlled release of the therapeutically active agent when the coated substrate is exposed to aqueous solutions such as gastric fluid, comprising subjecting the coated substrate to curing at a temperature and humidity level elevated above normal, ambient conditions and for such a time period that the coated substrate is rendered to a condition in which it provides a release rate of said therapeutically active agent which is substantially unaffected during storage by elevations in temperature and humidity.
25
30. The method of claim 29, further comprising preparing the coated substrate by applying said therapeutically active agent onto the surface of a pharmaceutically inert bead, and conducting the oven curing at a temperature above the glass transition temperature of the plasticized ethylcellulose coating and a relative humidity of about 85% for a time period from about 48 to about 72 hours.
30
31. A stabilized solid controlled release dosage form comprising a substrate comprising a therapeutically active agent, said substrate overcoated with a controlled release coating derived from an aqueous dispersion of ethylcellulose which has been stabilized by curing at a temperature and relative humidity elevated to a suitable level above ambient conditions for a time period necessary to obtain a final product which exhibits an in vitro release of said therapeutically active agent which is substantially unaffected by exposure to storage conditions of elevated temperature and/or elevated relative humidity.
35
40
45
50
55










FIGURE 5

Example 1
Hydromorphone HCl Dissolution
After 8 Weeks Storage at Different Conditions





FIGURE 6
Example 1
Initial Hydromorphone HCl Dissolution
After Various Curing Conditions





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 92 10 6519

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. CL.5)
Y	GB-A-2 170 104 (WARNER LAMBERT COMPANY) * page 1, line 32 - line 34 * * page 1, line 49 - line 54 * ---	1-9, 11-19,21	A61K9/50 A61K9/54
Y	D. L. MUNDAY, A. R. FASSIHI '5th Congr. int. technol. pharm. volume 2, changes in drug release rate, effect of temperature and relative humidity on polymeric film coatings' 1989, ASSOC. PHARM. GALENIQUE IND., CHATENAY MALABRY, FR * the whole document * -----	1-9, 11-19,21	
			TECHNICAL FIELDS SEARCHED (Int. CL.5)
			A61K
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 27 JANUARY 1993	Examiner VENTURA AMAT A.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	